

For welding steel such as:

| Outokumpu   | EN | ASTM | SS* | BS* | NF* |
|---|----|------|-----|-----|-----|
| Overalloyed electrode for surfacing unalloyed steel, joint welding non-molybdenum alloyed stainless steel to unalloyed steel and for welding clad material. |    |      |     |     |     |

\* Obsolete national standards, replaced by EN 10088.

#### Characteristics

AVESTA 309L-4D is an overalloyed electrode intended for welding stainless steel unalloyed or low-alloy steels. It has a thin, rutile-acid type coating and is designed for welding with either AC or positive polarity DC.

AVESTA 309L-4D has a composition that, under normal welding conditions, ensures a crack resistant weld metal.


AVESTA 309L-4D can also be used for welding some high temperature steels. Always consult expertise.

#### Welding directions

AVESTA 309L-4D is designed for the continuous welding of pipes.

The combination of low welding currents and good fluidity means that pipes with a wall thickness of 0.08 inch (2 mm) can be welded using an electrode with a diameter of 0.08 inch (2 mm).

Pipe welding can be performed in several different ways. One possibility is to start welding in overhead position (1), followed by vertical-down on both sides from 12 o'clock position (2 and 3). Another possibility is to start at the 7 o'clock position and weld vertical up to the 11 o'clock position on both sides. This requires an inverter power source with a remote control.



When welding stainless to unalloyed thin plates and pipes, DC- is often preferred.

Welding to primer-coated sheet should be avoided, as there is a significant risk of pore formation. The paint should therefore be removed from all surfaces that are likely to be exposed to temperatures above 932°F (500°C).

#### Packaging data

| Diam. inch | Diam. mm | Length mm/inch | Weight/capsule, lbs | Electrodes/capsule, approx. | Weight/carton, lbs |
|------------|----------|----------------|---------------------|-----------------------------|--------------------|
| 5/64       | 2.0      | 300 / 12       | 4.2                 | 173                         | 25                 |
| 3/32       | 2.5      | 300 / 12       | 4.2                 | 115                         | 25                 |
| 1/8        | 3.25     | 350 / 14       | 9.1                 | 123                         | 27                 |

Approvals: -

#### Standard designations

|          |             |
|----------|-------------|
| EN 1600  | E 23 12 L R |
| AWS A5.4 | E309L-17    |

#### Typical analysis % (All weld metal)

| C    | Si  | Mn  | Cr   | Ni   |
|------|-----|-----|------|------|
| 0.02 | 0.8 | 1.0 | 23.3 | 12.8 |

Ferrite 15 FN DeLong

#### Mechanical properties

|                                   | Typical values (IIW)  |          |
|-----------------------------------|-----------------------|----------|
| Yield strength, Rp <sub>0.2</sub> | 460 N/mm <sup>2</sup> | 68 ksi   |
| Tensile strength, R <sub>m</sub>  | 590 N/mm <sup>2</sup> | 86 ksi   |
| Elongation, A <sub>5</sub>        | 29 %                  | 29 %     |
| Impact strength, KV +20°C         | 50 J                  | 37 ft-lb |
| Hardness approx.                  | 210 Brinell           |          |

#### Welding data

| DC+/- or AC | Diam., inch | Current, A |
|-------------|-------------|------------|
|             | 5/64        | 25– 55     |
|             | 3/32        | 30– 85     |
|             | 1/8         | 45–110     |

**Interpass temperature:** Max. 300°F (150°C).

**Heat input:** Max. 50.8 kJ/in (2.0 kJ/mm).

**Heat treatment:** Generally none. For constructions that include low-alloy steels in mixed joints, a stress-relieving annealing stage may be advisable. However, this type of alloy may be susceptible to embrittlement-inducing precipitation in the temperature range 1022-1742°F (550-950°C). Always consult the supplier of the parent metal or seek other expert advice to ensure that the correct heat treatment process is carried out.

**Structure:** Austenite with 10-15% ferrite.

**Scaling temperature:** Approx. 1832°F (1000°C) (air).

**Corrosion resistance:** Superior to 308L. When surfacing mild steel a corrosion resistance equivalent to that of ASTM 304 is obtained already in the first bead.

#### Welding positions

